

Relatório de Ensaios

No. BR2202906 Rev. 1

Pag.1 de 4

HT MICRON SEMICONDUTORES S.A.
AVENIDA UNISINOS
1550
SAO LEOPOLDO, RS 93022750
BRAZIL

**** Este relatório anula e substitui a revisão anterior do Relatório No. BR2202906 emitido pela SGS em 09/08/22 ****

SGS Ordem No. : 40028181
Nome da amostra: eMCP
Total de Amostras Recebidas : 01 AMOSTRA

As amostra(s) e informações acima foram fornecidas pelo cliente.

Número da Proposta : C&P PR22-269462.22 rev.02
Data de Recebimento da Amostra: 21 Jul 2022
Período de análise : 25 Jul 2022 - 09 Ago 2022
Teste Solicitado : Teste(s) selecionado(s) conforme solicitado pelo cliente.
Método de ensaio : Consulte a(s) página(s) seguinte(s).
Resultados dos Ensaios : Consulte a(s) página(s) seguinte(s).
Responsabilidade Técnica : Alessandra Shimizu - Gerente de Laboratório CRQ 04245592

AVISO: As opiniões e interpretações expressas abaixo são baseadas nos resultados obtidos a partir do item ensaiado, aplicáveis somente para os ensaios em que os parâmetros de especificação estão inclusos nesse relatório.

Opiniões e Interpretações :

Baseado nos testes executados na amostra, o resultado **atende** aos requisitos estabelecidos pela Diretiva RoHS (UE) 2015/863 e emenda Anexo II da Diretiva 2011/65/UE, para os ensaios realizados.

Resumo de Resultados :

Teste Solicitado :	Método de Ensaio	Avaliação
Determinação de Chumbo, Cádmiio, Cromo e Mercúrio em Polímeros, Metais e Eletrônicos por ICP-OES	Referenciado nas IEC 62321-4:2013+A1:2017 e IEC 62321-5:2013, análise realizada por ICP-OES.	Atende
Determinação de Cromo Hexavalente em Polímeros e Eletrônicos por Método Colorimétrico	Referenciado na IEC 62321-7-2:2017; análise realizada por UV-VIS.	Atende
Determinação de PBB e PBDE em Polímeros por GC-MS	Referenciado na IEC 62321-6:2015, análise realizada por GC-MS.	Atende

Relatório de Ensaios

No. BR2202906 Rev. 1

Pag.2 de 4

Assina em nome da
SGS do Brasil Ltda.



Alessandra Shimizu
Gerente de Laboratório CRQ 04245592

This document is issued by the Company under its General Conditions of Service available on request and accessible at <http://www.sgsgroup.com.br/pt-br/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained as a confirmed on proposal. This document cannot be reproduced except in full, without prior written approval of the Company.

Relatório de Ensaios

No. BR2202906 Rev. 1

Pag.3 de 4

Resultados dos Ensaios :

Descrição das Amostras

Specimen No.	SGS ID Amostra	Descrição
1	BR2202906.001	eMCP

Nota :

- (1) MQL = Limite de Quantificação do Método
 (2) ND = Não Detectado (< MQL)
 (3) "-" = Análises em Processo
 (4) 1 mg/kg = 0,0001%
 (5) mg/kg = ppm

Determinação de Chumbo, Cádmio, Cromo e Mercúrio em Polímeros, Metais e Eletrônicos por ICP-OES

Metodologia Referenciado nas IEC 62321-4:2013+A1:2017 e IEC 62321-5:2013, análise realizada por ICP-OES.

Item(s) de Teste	Limite	Unid.	MQL	Incerteza	001
Chumbo (Pb)	Max. 1000,00	mg/kg	12,50	± 1,19	14,82
Cádmio (Cd)	Max. 100,00	mg/kg	12,50	NA	ND
Mercúrio (Hg)	Max. 1000,00	mg/kg	62,50	NA	ND

- As incertezas expandidas foram calculadas considerando k=2 e intervalo de confiança de ±95%.

Determinação de Cromo Hexavalente em Polímeros e Eletrônicos por Método Colorimétrico

Metodologia Referenciado na IEC 62321-7-2:2017; análise realizada por UV-VIS.

Item(s) de Teste	Limite	Unid.	MQL	Incerteza	001
Cromo Hexavalente - CrVI	Max. 1000,00	mg/kg	10,00	NA	ND

- As incertezas expandidas foram calculadas considerando k=2 e intervalo de confiança de ±95%.

Determinação de PBB e PBDE em Polímeros por GC-MS

Metodologia Referenciado na IEC 62321-6:2015, análise realizada por GC-MS.

Item(s) de Teste	Limite	Unid.	MQL	Incerteza	001
Monobromobifenil	-	mg/kg	35,00	NA	ND
Dibromobifenil	-	mg/kg	35,00	NA	ND
Tribromobifenil	-	mg/kg	35,00	NA	ND
Tetrabromobifenil	-	mg/kg	35,00	NA	ND
Pentabromobifenil	-	mg/kg	35,00	NA	ND
Hexabromobifenil	-	mg/kg	35,00	NA	ND
Heptabromobifenil	-	mg/kg	35,00	NA	ND
Octabromobifenil	-	mg/kg	35,00	NA	ND
Nonabromobifenil	-	mg/kg	35,00	NA	ND
Decabromobifenil	-	mg/kg	35,00	NA	ND
Soma dos PBBs	Max. 1000,00	mg/kg	-	NA	ND

This document is issued by the Company under its General Conditions of Service available on request and accessible at <http://www.sgsgroup.com.br/pt-br/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained as a confirmed on proposal. This document cannot be reproduced except in full, without prior written approval of the Company.

Relatório de Ensaio

No. BR2202906 Rev. 1

Pag.4 de 4

<u>Item(s) de Teste</u>	<u>Limite</u>	<u>Unid.</u>	<u>MQL</u>	<u>Incerteza</u>	<u>001</u>
Monobromodifenil Eter	-	mg/kg	50,00	NA	ND
DiBromoDifenil Eter	-	mg/kg	50,00	NA	ND
Tribromodifenil Eter	-	mg/kg	50,00	NA	ND
Tetrabromobifenil Eter	-	mg/kg	50,00	NA	ND
Pentabromodifenil Eter	-	mg/kg	50,00	NA	ND
Hexabromodifenil Eter	-	mg/kg	50,00	NA	ND
Hexabromodifenil Eter	-	mg/kg	50,00	NA	ND
Heptabromodifenil Eter	-	mg/kg	50,00	NA	ND
Octabromodifenil Eter	-	mg/kg	125,00	NA	ND
Nonabromodifenil Eter	-	mg/kg	125,00	NA	ND
Nonabromodifenil Eter	-	mg/kg	125,00	NA	ND
Nonabromodifenil Eter	-	mg/kg	125,00	NA	ND
Decabromodifenil Eter	-	mg/kg	125,00	NA	ND
Soma dos PBDEs	Max. 1000,00	mg/kg	-	NA	ND

- As incertezas expandidas foram calculadas considerando k=2 e intervalo de confiança de $\pm 95\%$.

Observações :

Os resultados reportados referem-se somente às amostras submetidas aos ensaios. A SGS não se responsabiliza pelas informações a respeito da composição da amostra e seus dados de fabricação. As mesmas são de responsabilidade exclusiva do cliente e não fazem parte do escopo de serviço da SGS do Brasil LTDA.

Este documento não pode ser reproduzido, exceto na íntegra, sem aprovação prévia por escrito da SGS.

A Regra de decisão definida pela SGS estabelece que a incerteza de medição não será considerada no Veredito (declaração de conformidade) quando indicado no relatório de ensaio.

Revisão 01: Conforme solicitado pelo cliente, o nome da amostra foi alterado de "eMCPC (V5+D1z)" para "eMCP".

*** Final do Relatório ***

Os ensaios foram realizados no laboratório SGS do Brasil, localizado no endereço citado no rodapé deste relatório.

Relatório de Ensaios

No. BR2202906-01 Rev. 1

Pag.1 de 2

HT MICRON SEMICONDUTORES S.A.
AVENIDA UNISINOS
1550
SAO LEOPOLDO, RS 93022750
BRAZIL

**** Este relatório anula e substitui a revisão anterior do Relatório No. BR2202906-01 emitido pela SGS em 09/08/22 ****

SGS Ordem No. : 40028181
Nome da amostra: eMCP
Total de Amostras Recebidas : 01 AMOSTRA

As amostra(s) e informações acima foram fornecidas pelo cliente.

Número da Proposta : C&P PR22-269462.22 rev.02
Data de Recebimento da Amostra: 21 Jul 2022
Período de análise : 25 Jul 2022 - 09 Ago 2022
Teste Solicitado : Teste(s) selecionado(s) conforme solicitado pelo cliente.
Método de ensaio : Consulte a(s) página(s) seguinte(s).
Resultados dos Ensaios : Consulte a(s) página(s) seguinte(s).
Responsabilidade Técnica : Alessandra Shimizu - Gerente de Laboratório CRQ 04245592

AVISO: As opiniões e interpretações expressas abaixo são baseadas nos resultados obtidos a partir do item ensaiado, aplicáveis somente para os ensaios em que os parâmetros de especificação estão inclusos nesse relatório.

Opiniões e Interpretações :

Baseado nos testes executados na amostra, o resultado **atende** aos requisitos estabelecidos pela Diretiva RoHS (UE) 2015/863 e emenda Anexo II da Diretiva 2011/65/UE, para os ensaios realizados.

Resumo de Resultados :

Teste Solicitado :	Método de Ensaio	Avaliação
Ftalatos	Referenciado na IEC 62321-8:2017 análise realizada por GC-MS.	Atende

Assina em nome da
SGS do Brasil Ltda.



Alessandra Shimizu
Gerente de Laboratório CRQ 04245592

Relatório de Ensaios

No. BR2202906-01 Rev. 1

Pag.2 de 2

Resultados dos Ensaios :

Descrição das Amostras

Specimen No.	SGS ID Amostra	Descrição
1	BR2202906-01.001	eMCP

Nota :

- (1) MQL = Limite de Quantificação do Método
- (2) ND = Não Detectado (< MQL)
- (3) "--" = Análises em Processo
- (4) 1 mg/kg =0,0001%
- (5) mg/kg = ppm

Ftalatos

Metodologia Referenciado na IEC 62321-8:2017 análise realizada por GC-MS.

<u>Item(s) de Teste</u>	<u>CAS NO.</u>	<u>Limite</u>	<u>Unid.</u>	<u>MQL</u>	<u>Incerteza</u>	<u>001</u>
Di(2-etilhexil) Ftalato (DEHP)	117-81-7	Max. 0,100	%	0,005	NA	ND
Benzil butil Ftalato (BBP)	85-68-7	Max. 0,100	%	0,005	NA	ND
Ftalato de di-n-butilo (DBP)	84-74-2	Max. 0,100	%	0,005	NA	ND
Di-isobutil Ftalato (DIBP)	84-69-5	Max. 0,100	%	0,005	NA	ND

- As incertezas expandidas foram calculadas considerando k=2 e intervalo de confiança de $\pm 95\%$.

Observações :

Os resultados reportados referem-se somente às amostras submetidas aos ensaios. A SGS não se responsabiliza pelas informações a respeito da composição da amostra e seus dados de fabricação. As mesmas são de responsabilidade exclusiva do cliente e não fazem parte do escopo de serviço da SGS do Brasil LTDA.

Este documento não pode ser reproduzido, exceto na íntegra, sem aprovação prévia por escrito da SGS.

A Regra de decisão definida pela SGS estabelece que a incerteza de medição não será considerada no Veredicto (declaração de conformidade) quando indicado no relatório de ensaio.

Revisão 01: Conforme solicitado pelo cliente, o nome da amostra foi alterado de "eMCPC (V5+D1z)" para "eMCP".

*** Final do Relatório ***

Os ensaios foram realizados no laboratório SGS do Brasil, localizado no endereço citado no rodapé deste relatório.

Test Report

No. HKTEC2204282102

Date: 07 Sep 2022

Page 1 of 5

HT MICRON SEMICONDUTORES S.A.
AVENIDA UNISINOS, 1550,
CRISTO REI,
SÃO LEOPOLDO

This report supersedes all previous documents bearing the test report number HKTEC2204282101 with amendment by changing the sample name on page 1 which is as per client request.

The following sample(s) was/were submitted and identified on behalf of the clients as : eMCP BR2202906EXT

SGS Job No. : 5102381 - HK
Date of Sample Received : 08 Aug 2022
Testing Period : 08 Aug 2022 - 17 Aug 2022
Test Requested : Selected test(s) as requested by client.
Test Method : Please refer to next page(s).
Test Results : Please refer to next page(s).
Conclusion : The test results of submitted sample(s) do not exceed the reference limit.

Signed for and on behalf of
SGS Hong Kong Limited.



Lam Ka Yung, Allen
Senior Chemist

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Test Report

No. HKTEC2204282102

Date: 07 Sep 2022

Page 2 of 5

Test Results :

Test Part Description :

Specimen No.	SGS Sample ID	Description
1	HKT22-042821.001	Black plastic w/ golden/ silvery metal w/ chips

Remarks :

- (1) 1 mg/kg = 1 ppm = 0.0001%
- (2) MDL = Method Detection Limit
- (3) ND = Not Detected (< MDL)
- (4) "-" = Not Regulated

Halogen

Test Method : With reference to EN 14582:2016, analysis was performed by IC.

Test Item(s)	Limit	Unit	MDL	001
Fluorine (F)	-	mg/kg	50	1500
Chlorine (Cl)	-	mg/kg	50	ND
Bromine (Br)	-	mg/kg	50	ND
Iodine (I)	-	mg/kg	50	ND

Notes :

- (1) The measurement report of the expanded uncertainty with confident level 95% by coverage factor k=2, is 20% for each analyte of halogen.

IEC61249-2-21 - Halogen

Test Method : With reference to EN 14582: 2016, determination by Ion Chromatograph (IC) method. (Decision Rule: please refer to appendix 1: Category 1)

Test Item(s)	Limit	Unit	MDL	001
Chlorine (Cl)	900	mg/kg	50	ND
Bromine (Br)	900	mg/kg	50	ND
Chlorine (Cl)+Bromine (Br)	1,500	mg/kg	100	ND

Conclusion

PASS

Notes :

The reference limit is referred from IEC61249-2-21.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Appendix 1


Category	Decision Rule Statement
1	<p>The decision rule for conformity reporting is based on the non-binary statement with guard band (is equal to the expanded measurement uncertainty with a 95% coverage probability, $w = U95$) in ILAC-G8:09/2019 Clause 4.2.3.</p> <p>A. "Pass - the measured value is within (or below / above) the acceptance limit, where the acceptance limit is below / above to the guard band." or "Pass - The measured values were observed in tolerance at the points tested. The specific false accept risk is up to 2.5%."</p> <p>B. "Conditional Pass - The measured values were observed in tolerance at the points tested. However, a portion of the expanded measurement uncertainty intervals about one or more measured values exceeded / out of tolerance. When the measured result is close to the tolerance, the specific false accept risk is up to 50%."</p> <p>C. "Conditional Fail - One or more measured values were observed out of tolerance at the points tested. However, a portion of the expanded measurement uncertainty intervals about one or more measured values were in tolerance. When the measured result is close to the tolerance, the specific false reject risk is up to 50%."</p> <p>D. "Fail - the measured value is out of (or below / above) the tolerance limit added / subtracted to the guard band." or "Fail - One or more measured values were observed out of tolerance at the points tested". The specific false reject risk is up to 2.5%.</p>
2	<p>The decision rule for conformity reporting is based on BS EN 1811:2011+A1:2015: Reference test method for release of nickel from all post assemblies which are inserted into pierced parts of the human body and articles intended to come into direct and prolonged contact with the skin in Section 9.2 interpretation of results.</p>
3	<p>The decision rule for conformity reporting is based on the general consideration of simple acceptance as stated in ISO/IEC Guide 98-3: "Uncertainty of measurement - Part 3: Guide to the expression of uncertainty in measurement (GUM 1995)", and more specifically for analytical measurements to the EURACHEM/CITAC Guide 2012 "Quantifying Uncertainty in Analytical Measurement".</p>
4	<p>The decision rule for conformity reporting is according to the IEC 62321-7-1 Edition 1.0 2015-09 Section 7: Table 1-(comparison to standard and interpretation of result)</p>
5	<p>The decision rule for conformity reporting is according to the IEC 62321-3-1 Edition 1.0 2013-06 Annex A.3 interpretation of result.</p>
6	<p>The decision rule for conformity reporting is according to the GB/T 26125-2011 Annex A to H</p>
7	<p>The decision rule for conformity reporting is according to the requested specification or standard (ASTM F963-17 section 4.3.5)</p>
8	<p>The decision rule for conformity reporting is according to the requested specification or standard (AS/NZS ISO 8124 Part 3 section 4.2)</p>
Remark	<p>If the decision rule is not feasible to be used and the uncertainty of the result is able to be provided, the uncertainty range of the result will be shown in the report. Otherwise, only result will be shown in the report.</p>

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Flowchart for Halogen Free Test

Method: BS EN14582:2016




Operator: Tang Ying Sam
Supervisor: Chan Chun Kit (Dickson)

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Relatório de Ensaios

No. BR2202906-02 Rev. 0

Data: Barueri, 10 Ago 2022

Pag.1 de 2

HT MICRON SEMICONDUTORES S.A.
AVENIDA UNISINOS
1550
SAO LEOPOLDO, RS 93022750
BRAZIL

SGS Ordem No. : 40028181

SGS ID Amostra BR2202906-02.001
Descrição eMCP

Total de Amostras Recebidas : 01 AMOSTRA

As informações acima foram fornecidas pelo cliente ou em seu nome.

Número da Proposta : C&P PR22-269462.22 rev.02
Data de Recebimento da Amostra: 21 Jul 2022
Período de análise : 25 Jul 2022 - 10 Ago 2022
Teste Solicitado : Teste(s) selecionado(s) conforme solicitado pelo cliente.
Descrição das Amostras: Consulte a(s) página(s) seguinte(s).
Método de ensaio : Consulte a(s) página(s) seguinte(s).
Resultados dos Ensaios : Consulte a(s) página(s) seguinte(s).
Responsabilidade Técnica : Alessandra Shimizu - Gerente de Laboratório CRQ 04245592

Assina em nome da
SGS do Brasil Ltda.



Alessandra Shimizu
Gerente de Laboratório CRQ 04245592

This document is issued by the Company under its General Conditions of Service available on request and accessible at <http://www.sgsgroup.com.br/pt-br/terms-and-conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained as a confirmed on proposal. This document cannot be reproduced except in full, without prior written approval of the Company.

Resultados dos Ensaios :

Descrição das Amostras :

Item No.	SGS ID Amostra	Descrição
1	BR2202906.001	eMCP

Metais Pesados

Método de ensaio : Referenciado na US EPA 3052:1996, análise foi realizada por ICP-OES.

<u>Item(s) de Teste</u>	<u>Limite</u>	<u>MQL</u>	<u>Unid.</u>	001
Antimônio (Sb)	-	12,50	mg/kg	ND

Ácido Perfluorooctanico (PFOA) e Ácido Heptadecafluorooctano Sulfônico (PFOS)

Método de ensaio : Método In House 2364/12. Análise realizada por LC-MS.

<u>Item(s) de Teste</u>	<u>CAS NO.</u>	<u>Limite</u>	<u>MQL</u>	<u>Unid.</u>	001
Ácido perfluorooctanóico (PFOA)	335-67-1	-	1,000	µg/m ²	ND
Perfluorooctanosulfonatos (PFOS)	1763-23-1	-	1,000	µg/m ²	ND

Nota :

- (1) MQL = Limite de Quantificação do Método
- (2) ND = Não Detectado (< MQL)
- (3) "-" = Não Analisado / Não Aplicável
- (4) "--" = Análises em Processo
- (5) 1 mg/kg =0,0001%
- (6) mg/kg = ppm

Observações :

Os resultados reportados referem-se somente às amostras submetidas aos ensaios. A SGS não se responsabiliza pelas informações a respeito da composição da amostra e seus dados de fabricação. As mesmas são de responsabilidade exclusiva do cliente e não fazem parte do escopo de serviço da SGS do Brasil LTDA.

Este documento não pode ser reproduzido, exceto na íntegra, sem aprovação prévia por escrito da SGS.

A Regra de decisão definida pela SGS estabelece que a incerteza de medição não será considerada no Veredicto (declaração de conformidade) quando indicado no relatório de ensaio.

Opiniões e Interpretações :

*** Final do Relatório ***

Os ensaios foram realizados no laboratório SGS do Brasil, localizado no endereço citado no rodapé deste relatório.